

Typical data for SURA® M250-35A

T	W/kg at 50 Hz	VA/kg at 50 Hz	A/m at 50 Hz	W/kg at 100 Hz	W/kg at 200 Hz	W/kg at 400 Hz	W/kg at 1000 Hz	W/kg at 2500 Hz
0,1	0,02	0,06	26,8	0,04	0,08	0,21	0,98	4,09
0,2	0,06	0,15	35,7	0,14	0,33	0,90	3,65	14,8
0,3	0,13	0,27	41,8	0,31	0,73	1,93	7,58	30,6
0,4	0,21	0,40	47,5	0,51	1,23	3,24	12,7	51,7
0,5	0,31	0,56	53,4	0,75	1,82	4,81	18,8	78,8
0,6	0,41	0,74	60,0	1,01	2,49	6,69	26,3	113
0,7	0,52	0,95	67,9	1,31	3,26	8,82	35,2	155
0,8	0,66	1,21	77,5	1,64	4,12	11,2	45,7	208
0,9	0,81	1,52	90,0	2,00	5,07	14,0	58,1	273
1,0	0,98	1,92	107	2,41	6,14	17,1	72,6	352
1,1	1,15	2,46	133	2,87	7,33	20,6	89,6	
1,2	1,37	3,30	179	3,40	8,69	24,6		
1,3	1,65	4,97	284	4,03	10,3	29,2		
1,4	2,00	10,3	642	4,83	12,4	35,1		
1,5	2,35	30,0	1810	5,72	14,7	41,6		
1,6	2,65	75,7	4030					
1,7	2,87	153	7290					
1,8	3,06	267	11700					

Loss at 1.5 T , 50 Hz, W/kg 2,35

Loss at 1.0 T , 50 Hz, W/kg 0,98

Anisotropy of loss, % 10

Magnetic polarization at 50 Hz

H = 2500 A/m, T 1,53

H = 5000 A/m, T 1,64

H = 10000 A/m, T 1,76

Coercivity (DC), A/m 40

Relative permeability at 1.5 T 660

Resistivity, $\mu\Omega\text{cm}$ 55

Yield strength, N/mm² 455

Tensile strength, N/mm² 575

Young's modulus, RD, N/mm² 185 000

Young's modulus, TD, N/mm² 200 000

Hardness HV5 (VPN) 215



RD represents the rolling direction

TD represents the transverse direction

Values for yield strength (0.2 % proof strength)

and tensile strength are given for the rolling direction

Values for the transverse direction are approximately 5% higher