

Ympress® S550MC

Strong, consistent and highly formable

Ympress® S550MC is a hot-rolled, high-strength low-alloy steel. It combines high strength with outstanding formability and consistent quality. It is ideal for applications where high strength is essential. These include large cranes, earthmoving equipment and telescopic booms.

The high yield strength of Ympress® S550MC delivers improved load-bearing capacity without weight penalties. Its strength also enables production of lighter components for applications where

weight savings are a prime consideration. Down-gauging offers an additional benefit of increased yield per tonne of steel. Consistent product properties and reliable material thickness allow trouble-free, repeatable processing. Ympress® S550MC can be easily welded and galvanised. Its high surface quality can lead to fewer processing steps.

Mechanical properties (parallel to the rolling direction)

| | Min. yield strength | Min. - Max. tensile strength | Elongation after fracture A | | | Min bending radius* | |
|---------------|------------------------|------------------------------|-----------------------------|--|--|---------------------|---------|
| | | | t < 3mm | 3mm ≤ t < 5mm | t ≥ 5mm | t < 5mm | t ≥ 5mm |
| | R _{eh} in MPa | R _m in MPa | L ₀ =80mm (%) | L ₀ =5.65√S ₀ mm (%) | L ₀ =5.65√S ₀ mm (%) | (t) | (t) |
| Typical value | 600 | 660 | 20 | 22 | 22 | - | - |
| Guaranteed | 550 | 610-750 | ≥ 13 | ≥ 17 | ≥ 17 | 0.5 | 0.5 |
| EN 10149-2 | 550 | 600-760 | ≥ 12 | ≥ 14 | ≥ 14 | 1.5 | 1.5 |

* minimum 180° bend radius, measured transverse to the rolling direction

Chemical composition (% by weight)

| | C | Mn | Si | P | S | Al _{tot} | Nb | V | Ti | Mo | Ceq* |
|------------|--------|--------|--------|---------|---------|-------------------|--------|--------|--------|----|------|
| Guaranteed | ≤ 0.10 | ≤ 1.65 | ≤ 0.03 | ≤ 0.020 | ≤ 0.003 | ≥ 0.015 | ≤ 0.09 | - | ≤ 0.06 | - | 0.33 |
| EN 10149-2 | ≤ 0.12 | ≤ 1.80 | ≤ 0.50 | ≤ 0.025 | ≤ 0.015 | ≥ 0.015 | ≤ 0.09 | ≤ 0.20 | ≤ 0.15 | - | - |

* Ceq is a typical value

Impact strength (optional and parallel to the rolling direction)

| | Impact test in J at -20°C |
|--------------------|---------------------------|
| Guaranteed (6-8mm) | ≥ 40 |
| Typical value | 140 |

* in accordance with EN 10149 the impact values above are only guaranteed if accepted on order

Tolerances on thickness

All Ympress® products comply to ½ EN 10051:2010. Tighter tolerances are available on request.

Certification

A 2.2 certificate is issued as standard with Ympress® products. Other certificate types are available on request.


Product support

We want you to get the best from Ympress® products. Our technical engineers and trained sales staff are always happy to answer your questions on steel selection and application. Our engineers are available to assist you with process and product design optimisation for improved throughput, yield and end-product performance.

Product Range

| | |
|--------------------|--|
| Ympress®: | S315MC, S355MC, S420MC, S460MC, S500 MC, S550MC S650MC, E690TM, S700MC |
| Ympress® Laser: | E250C / S355MC / S420MC |
| Thickness range: | 1.5 - 20mm (grade specific) |
| Width range: | 750 - 2070mm (grade specific) |
| Surface treatment: | Hot rolled dry, pickled & oiled |

Available dimensions of Ympress® S550MC



www.tatasteeleurope.com

Tata Steel

PO Box 10.000
1970 CA IJmuiden
The Netherlands
T: +31 (0)251 496126
E: strip.enquiries@tatasteel.com

CT0515:IS:PDF:ENG:0714

While care has been taken to ensure that the information contained in this publication is accurate, neither Tata Steel Europe Limited, nor its subsidiaries, accept responsibility or liability for errors or for information which is found to be misleading.

Tata Steel Europe Limited is registered in England under number 0595756 with registered office at 30 Millbank, London, SW1P 4WY

Copyright 2014
Tata Steel Europe Limited