

**Declaration of Performance**  
(according to regulation EU No 305/2011)

Certificate No:

2814/CPR/RQA0532073/A

S355JR

**Strip S355JR / 1.0045 according EN 10025-2**

To be used in-welded, bolted and riveted structures


Tata Steel IJmuiden B.V.  
Wenckebachstraat 1  
1951 JZ Velsen-Noord  
The Netherlands  
Tel: +31 251 49111  
Website : [www.tatasteeleurope.com](http://www.tatasteeleurope.com)

CE Marking Notified Body  
Lloyd's Register Verification B.V.  
K.P. Van Der Mandelelaan 41 A  
3062 MB Rotterdam  
The Netherlands

System of assessment and verification of constancy of  
performance of the product  
System 2+

Notified factory production control certification body No. 2814  
performed the initial inspection of the manufacturing plant and of  
factory production control and the continuous surveillance,  
assessment, and evaluation of factory production control and  
issued the certificate of conformity of the factory production  
control

The performance of the product identified is in conformity with  
the declared performance. This declaration of performance is  
issued, in accordance with regulation (EU) No305/2011, under  
the sole responsibility of the manufacturer. Signed for and on  
behalf of the manufacturer by:



Carel Kleemans – Technical Director, Strip Products MLE 5<sup>th</sup> of August 2021  
Tata Steel IJmuiden BV Date

Essential characteristic	Performance		Harmonised technical specification
Tolerances on dimensions and shape	Dimensions	EN 10051	
Yield strength (transverse)	Flatness	EN10051	
	Nominal thickness (mm)	Values Min (MPa)	
	>	<=	
	1.4	16	355
	16	20	345
Tensile strength (transverse)	Nominal thickness (mm)	Values (MPa)	
	>	<=	min max
	1.4	3	510 680
	3	20	470 630
Elongation (transverse)	Nominal thickness (mm)	Values min (%; 80mm)	
	>	<=	
	1.4	1.5	15
	1.5	2	16
	2	2.5	17
	2.5	3	18
	Nominal thickness (mm)	Values min (%; 5.65√so)	
	>3	<=20	22
Impact strength (longitudinal)	JR	27J at +20°C	
Weldability CEV	Nominal thickness (mm)	Values max (%)	
	>	<=	
	1.4	20	0.45
Durability	Nominal thickness (mm)	Values max (%)	
	>1.4	<=20	C:0,24 Si:0,55 Mn: 1,60 P: 0,035 S: 0,035 N:0,012 Cu: 0,55

EN10025-1 2004



2814

Tata Steel IJmuiden B.V.  
Wenckebachstraat 1  
1951 JZ Velsen-Noord  
The Netherlands

21

MLE Strip S355JR

EN 10025-1 – 2004

Strip S355JR/1.0045

To be used in-welded, bolted and riveted structures

Tolerances on dimensions : Strip EN10051

Elongation :  
Tensile Strength :  
Yield Strength : EN10025-2  
Impact Strength :  
Weldability :  
Durability :

Dangerous Substances : No Performance Determined