



## NO35-1750H Data sheet

thin non-oriented electrical steel

The Hi-Lite grade NO35-1750H fulfils all requirements in the standards EN 10303:2015 and IEC 60404-8-8:2017. In many cases the minimum / maximum properties are better than those of the grades with the same nominal thickness in these standards.

### Magnetic properties

	Min / Max values	Typical values
Specific total loss at 1.0 T and 50 Hz	-	0.88 W/kg
Specific total loss at 1.5 T and 50 Hz	-	2.11 W/kg
Specific total loss at 1.0 T and 400 Hz	Max 17.5 W/kg	16.4 W/kg
Specific total loss at 1.5 T and 400 Hz	Max 41.7 W/kg	38.8 W/kg
Specific total loss at 1.0 T and 700 Hz	Max 42.2 W/kg	39.4 W/kg
Specific total loss at 1.0 T and 2500 Hz	-	333 W/kg
Peak magnetic polarisation at 2500 A/m and 50 Hz	Min 1.52 T	1.56 T
Peak magnetic polarisation at 5000 A/m and 50 Hz	Min 1.62 T	1.65 T
Peak magnetic polarisation at 10000 A/m and 50 Hz	Min 1.74 T	1.77 T
Relative peak permeability at 1.5 T and 50 Hz	-	820
Relative peak permeability at 1.0 T and 400 Hz	-	6370

Guaranteed values for losses are maximum total specific losses and guaranteed values for magnetic polarisations are minimum peak polarisations

### Physical and mechanical properties

Nominal thickness 0.35 mm  
Density (assumed) 7.60 kg/dm<sup>3</sup>

	Min / Max values	Typical values
Electrical resistivity at 23 °C	-	59 μΩ·cm
Thermal conductivity at 23 °C	-	21 W/(m·K)
Thermal expansion 0-100 °C	-	12·10 <sup>-6</sup> /°C
Yield strength R <sub>p0.2</sub>	Min 390 MPa	435 MPa
Tensile strength R <sub>m</sub>	Min 500 MPa	535 MPa
Elongation at fracture A <sub>80</sub>	Min 12 %	17 %
Young's modulus	-	185 GPa

Values for the yield strength, tensile strength and Young's modulus are given for the rolling direction. Corresponding values for the transverse direction are approximately 2 % higher.

For more information and contact:  
[www.hi-lite.se](http://www.hi-lite.se)  
[www.tatasteeleurope.com](http://www.tatasteeleurope.com)  
[sales@sura.se](mailto:sales@sura.se)



## NO35-1750H Data sheet

thin non-oriented electrical steel

### Typical specific total loss

J <sub>peak</sub> (T)	Typical specific total loss (W/kg)								
	50 Hz	100 Hz	200 Hz	400 Hz	700 Hz	1000 Hz	2500 Hz	5000 Hz	10000 Hz
0.1	0.02	0.04	0.09	0.24	0.56	1.00	4.35	13.4	39.6
0.2	0.06	0.14	0.35	0.92	2.12	3.63	15.1	45.2	133
0.3	0.13	0.29	0.73	1.93	4.39	7.49	30.9	92.0	275
0.4	0.20	0.48	1.21	3.20	7.33	12.5	51.8	156	
0.5	0.29	0.69	1.76	4.73	10.9	18.7	78.1	239	
0.6	0.38	0.93	2.40	6.50	15.1	26.0	111	349	
0.7	0.49	1.20	3.12	8.54	19.9	34.6	151		
0.8	0.61	1.49	3.93	10.8	25.6	44.6	201		
0.9	0.74	1.81	4.81	13.4	32.0	56.4	261		
1.0	0.88	2.17	5.76	16.4	39.4	70.0	333		
1.1	1.04	2.58	6.85	19.6	47.8	85.8	424		
1.2	1.23	3.04	8.08	23.2	57.4	104			
1.3	1.47	3.61	9.56	27.5	68.5	125			
1.4	1.77	4.34	11.4	32.8	81.4	150			
1.5	2.11	5.15	13.5	38.8	96.6	177			
1.6	2.41	5.85	15.5	44.5	111	204			
1.7	2.68	6.53							
1.8	3.02	7.18							
1.9	3.46	8.07							

### Typical peak magnetic polarisation (magnetisation curve)

H <sub>peak</sub> (A/m)	Typical peak magnetic polarisation, J <sub>peak</sub> (T)								
	50 Hz	100 Hz	200 Hz	400 Hz	700 Hz	1000 Hz	2500 Hz	5000 Hz	10000 Hz
20	0.077	0.073	0.064	0.064	0.064	0.055	0.036	0.024	0.016
30	0.19	0.17	0.15	0.12	0.10	0.083	0.051	0.034	0.022
50	0.60	0.54	0.43	0.30	0.22	0.18	0.10	0.063	0.039
70	0.85	0.82	0.72	0.52	0.37	0.30	0.15	0.093	0.057
100	1.06	1.05	1.00	0.81	0.60	0.48	0.26	0.15	0.090
150	1.21	1.20	1.19	1.16	0.93	0.77	0.44	0.27	0.16
200	1.27	1.27	1.26	1.26	1.19	0.99	0.59	0.38	0.24
400	1.38	1.38	1.37	1.37	1.35	1.31	1.02	0.70	0.48
800	1.44	1.44	1.44	1.44	1.43	1.41	1.31		
1500	1.50	1.50	1.50	1.50	1.50	1.50			
2500	1.56	1.56	1.56	1.56	1.56	1.56			
5000	1.65	1.65	1.65	1.65	1.65	1.65			
7500	1.72	1.72							
10000	1.77	1.77							
20000	1.89	1.89							

For more information and contact:

[www.hi-lite.se](http://www.hi-lite.se)

[www.tatasteeleurope.com](http://www.tatasteeleurope.com)

[sales@sura.se](mailto:sales@sura.se)

**TATA STEEL**

The information and data in this data sheet is accurate to the best of Surahammars Bruk's knowledge but are intended for general information only. Surahammars Bruk and its businesses accept no liability for errors or information which is found to be misleading.